

FORM PTO-1390
(REV. 12-2001)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371ATTORNEY'S DOCKET NUMBER
D078 1160.1

U.S. APPLICATION NO. (If known, see 37 CFR 1.5

Not yet assigned
10/031217INTERNATIONAL APPLICATION NO.
PCT/EP00/06573 ✓INTERNATIONAL FILING DATE
11 July 2000 ✓PRIORITY DATE CLAIMED
21 July 1999 ✓

TITLE OF INVENTION

METHOD FOR PRODUCING FLAT ARTICLES FROM RENEWABLE RAW MATERIALS

APPLICANT(S) FOR DO/EO/US

Bernd Fischer; Heiko Hamann; Hans-Jorg Mauk; Miko Ess; Bernd Kastl

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). Unsigned
10. ☒ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
14. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:

PCT/IPEA/416

Cited References

PCT/IPEA/409

Certificate of Express Mail

PCT/ISA/210

PCT/ISA/220

U.S. APPLICATION NO. <u>10/031217</u> No. <u>031217</u> assigned		INTERNATIONAL APPLICATION NO. PCT/EP00/06573		ATTORNEY'S DOCKET NUMBER D078 1160.1	
---	--	---	--	---	--

21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1040.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$740.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS PTO USE ONLY	
				\$	890
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	\$	
Total claims	18 - 20 =	0	x \$18.00	\$	0
Independent claims	1 - 3 =	0	x \$84.00	\$	0
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				\$	0
TOTAL OF ABOVE CALCULATIONS =				\$	890
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	0
SUBTOTAL =				\$	890
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	0
TOTAL NATIONAL FEE =				\$	890
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	
TOTAL FEES ENCLOSED =				\$	890.00
				Amount to be refunded:	\$
				charged:	\$

a. ☐ A check in the amount of \$ _____ to cover the above fees is enclosed.

b. ☒ Please charge my Deposit Account No. 09-0528 in the amount of \$ 890.00 to cover the above fees.
 A duplicate copy of this sheet is enclosed.


c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
 overpayment to Deposit Account No. 09-0528. A duplicate copy of this sheet is enclosed.

d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card
 information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

WOMBLE CARLYLE SANDRIDGE & RICE
 Steven L. Schmid
 P.O. Box 7037
 Atlanta, GA 30357-0037



 SIGNATURE
 Steven L. Schmid

 NAME
 39,358

 REGISTRATION NUMBER

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In Re Application of:)	
)	
Bernd Fischer; Heiko Hamann;)	Examiner: Unknown
Hans-Jörg Mauk; Miko Ess;)	
and Bernd Kastl)	
)	
Serial No.: To Be Determined)	Art Unit: Unknown
)	
(National Phase of PCT/EP00/06573))	
)	
Filed: Herewith)	
)	Docket No.: D078 1160.1
For: METHOD FOR PRODUCING FLAT)	
ARTICLES FROM RENEWABLE RAW)	
MATERIALS)	

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Box PCT
Washington, D.C. 20231

Sir:

Please amend the subject application as follows:

IN THE CLAIMS

Please substitute the following amended claims 1-18 as set forth below, for claims 1-18 as originally filed in the above-identified application. A copy of the amended claims showing the amendments made thereto, including additions being shown with underlining and deletions being shown in brackets, is attached in the appendix herewith.

1. (Amended) A method for producing a flat article comprising a material that contains polyreaction products, comprising the following steps:
 - (1) Compounding of an epoxidation product of at least one carboxylic acid ester using at least one crosslinking agent,

(2) Pre-crosslinking of the mixture obtained in step (1) to form a moldable material,

(3) Molding of the moldable material obtained in step (2) in the shape of a flat article, and

(4) Curing of the molded material to produce the flat article, wherein the pre-crosslinking reaction in step (2) is separate from the curing reaction in step (4).


2. (Amended) The method according to Claim 1, wherein an epoxidized carboxylic acid ester of unsaturated fatty acids is used as the epoxidation product.
3. (Amended) The method according to Claim 1, wherein epoxidized linseed oil, epoxidized soybean oil, epoxidized castor oil, epoxidized rapeseed oil, vernonia oil or a mixture thereof containing at least two different epoxidation products is used as the epoxidation product.
4. (Amended) The method according to Claim 1, wherein the pre-crosslinking is carried out essentially by reacting the epoxy groups of the epoxidation product.
5. (Amended) The method according to Claim 1, wherein a di- or polycarboxylic acid, a derivative thereof, or a mixture containing at least two different crosslinking agents is used as the crosslinking agent.
6. (Amended) The method according to Claim 5, wherein maleic acid, itaconic acid, fumaric acid, succinic acid, methylsuccinic acid, malic acid, phthalic acid, tartaric acid, citraconic acid, furandicarboxylic acid, or a mixture of at least two of said acids is used as the dicarboxylic acid.
7. (Amended) The method according to Claim 6, wherein citric acid, trimellitic acid, or aconitic acid is used as the polycarboxylic acid.
8. (Amended) The method according to Claim 5, wherein an anhydride or partial ester is used as the derivative of a di- or polycarboxylic acid.

9. (Amended) The method according to Claim 1, wherein the reaction of the epoxidation product with the crosslinking agent is induced thermally, by radiation, or a combination thereof.
10. (Amended) The method according to Claim 9, wherein the reaction induced by radiation is carried out by using UV radiation in the presence of at least one UV initiator, by using electron beam radiation optionally in the presence of at least one UV initiator, and/or by using IR radiation, or a combination thereof.
11. (Amended) The method according to Claim 1, wherein an additional compounding step is included before step (3).
12. (Amended) The method according to Claim 1, wherein in step (1) or before step (3) at least one additional additive from the group comprising fillers, pigments, hydrophobing agents, and auxiliary agents is incorporated by compounding.
13. (Amended) The method according to Claim 1, wherein the curing of the moldable material is performed by peroxidic crosslinking via radical hydrogen abstraction, by radical polymerization of unsaturated double bonds, or combinations thereof.
14. (Amended) The method according to Claim 13, wherein the hydrogen abstraction and/or radical polymerization of unsaturated double bonds is initiated by radical-forming initiators selected from organic peroxides or azobis compounds or a mixture thereof.
15. (Amended) The method according to Claim 14, wherein the radical-forming initiators are incorporated by compounding in step (1) and/or before step (2) and/or before step (3).
16. (Amended) The method according to Claim 1, wherein pre-crosslinking and curing are carried out at different temperatures.
17. (Amended) A moldable material that can be stored, and which is obtained by steps (1) and (2) of the method as defined in Claim 1.

18. (Amended) A flat article obtained by the method as defined in Claim 1.

1/15/01
Date

Respectfully submitted,


Steven L. Schmid

Registration No. 39,358

James F. Vaughan

Registration No. 31,889

WOMBLE CARLYLE SANDRIDGE & RICE

P. O. Box 7037

Atlanta, Georgia 30357-0037

(404) 962-7539 (Telephone)

(404) 870-8234 (Facsimile)

EXPRESS MAIL

I hereby certify that this correspondence is being deposited with the United States Postal Service as "Express Mail Post Office To Addressee," in an envelope addressed to: Assistant Commissioner for Patents, Box PCT, Washington, D.C. 20231 on Jan. 15, 2002.

Express Mail No. EL759 079486 US.

Vandice Depalt
Signature

APPENDIX

1. (Amended) [Method] A method for producing a flat article comprising a material that contains polyreaction products, comprising the following steps:
 - (1) Compounding of an epoxidation product of at least one carboxylic acid ester using at least one crosslinking agent,
 - (2) Pre-crosslinking of the mixture obtained in step (1) to form a moldable material,
 - (3) Molding of the moldable material obtained in step (2) in the shape of a flat article, and
 - (4) Curing of the molded material to produce the flat article, wherein the pre-crosslinking reaction in step (2) is separate from the curing reaction in step (4).
2. (Amended) [Method] The method according to Claim 1, [characterized in that] wherein an epoxidized carboxylic acid ester of unsaturated fatty acids is used as the epoxidation product.
3. (Amended) [Method] The method according to Claim 1 [or 2], [characterized in that] wherein epoxidized linseed oil, epoxidized soybean oil, epoxidized castor oil, epoxidized rapeseed oil, [or] vernonia oil or a mixture thereof containing at least two different epoxidation products is used as the epoxidation product.
4. (Amended) [Method] The method according to [one Claims 1 through 3] Claim 1, [characterized in that] wherein the pre-crosslinking is carried out essentially by reacting the epoxy groups of the epoxidation product.
5. (Amended) [Method] The method according to [one Claims 1 through 4] Claim 1, [characterized in that] wherein a di- or polycarboxylic acid, [or] a derivative thereof, or a mixture containing at least two different crosslinking agents is used as the crosslinking agent.

6. (Amended) [Method] The method according to Claim 5, [characterized in that] wherein maleic acid, itaconic acid, fumaric acid, succinic acid, methylsuccinic acid, malic acid, phthalic acid, tartaric acid, citraconic acid, furandicarboxylic acid, or a mixture of at least two of said acids is used as the dicarboxylic acid.
7. (Amended) [Method] The method according to Claim 6, [characterized in that] wherein citric acid, trimellitic acid, or aconitic acid is used as the polycarboxylic acid.
8. (Amended) [Method] The method according to [one of Claims 5 through 7] Claim 5, [characterized in that] wherein an anhydride or partial ester is used as the derivative of a di- or polycarboxylic acid.
9. (Amended) [Method] The method according to [one of the preceding claims] Claim 1, [characterized in that] wherein the reaction of the epoxidation product with the crosslinking agent is induced thermally, [and/or] by radiation, or a combination thereof.
10. (Amended) [Method] The method according to Claim 9, [characterized in that] wherein the reaction induced by radiation is carried out by using UV radiation in the presence of at least one UV initiator, [and/or] by using electron beam radiation optionally in the presence of at least one UV initiator, and/or by using IR radiation, or a combination thereof.
11. (Amended) [Method] The method according to [one of the preceding claims] Claim 1, [characterized in that] wherein an additional compounding step is included before step (3).
12. (Amended) [Method] The method according to [one of the preceding claims] Claim 1, [characterized in that] wherein in step (1) or before step (3) at least one additional additive from the group comprising fillers, pigments, hydrophobing agents, and auxiliary agents is incorporated by compounding.
13. (Amended) [Method] The method according to [one of the preceding claims] Claim 1, [characterized in that] wherein the curing of the moldable material is performed by peroxidic crosslinking via radical hydrogen abstraction, [and/or] by radical polymerization of unsaturated double bonds, or combinations thereof.

14. (Amended) [Method] The method according to Claim 13, [characterized in that] wherein the hydrogen abstraction and/or radical polymerization of unsaturated double bonds is initiated by radical-forming initiators selected from organic peroxides or azobis compounds or a mixture thereof.
15. (Amended) [Method] The method according to Claim 14, [characterized in that] wherein the radical-forming initiators are incorporated by compounding in step (1) and/or before step (2) and/or before step (3).
16. (Amended) [Method] The method according to [one of the preceding claims] Claim 1, [characterized in that] wherein pre-crosslinking and curing are carried out at different temperatures.
17. (Amended) [Moldable] A moldable material that can be stored, and which [can be] is obtained by steps (1) and (2) of the method as defined in [Claims 1 through 16] Claim 1.
18. (Amended) [Flat] A flat article [which can be] obtained by the method as defined in [Claims 1 through 16] Claim 1.

Method for Producing Flat Articles
from Renewable Raw Materials

Description

The present invention relates to a method for producing a flat article comprising a material that contains polyreaction products. The method comprises the following steps: carrying out pre-crosslinking of a mixture comprising an epoxidation product of at least one carboxylic acid ester using at least one crosslinking agent to form a moldable material; molding the moldable material in the shape of a flat article; and curing the molded material to produce a flat article, wherein the pre-crosslinking reaction is separate from the curing reaction. The invention further relates to a moldable material that can be stored and to a flat article that can be obtained therefrom.

Linoleum has long been known as a resilient floor covering based on renewable raw materials. Because of its natural constituents, linoleum has achieved great importance based on its biological suitability for use in construction as well as environmental considerations. However, in the production of linoleum coverings the last step of the process requires a heat treatment, the so-called "ripening time," that lasts several weeks. Although measures have been undertaken in the prior art to shorten this ripening time and thus achieve higher productivity, continuous methods for producing linoleum flooring are thus far unknown in the art.

For this reason flat articles, based on renewable raw materials, that are composed of other materials have been described in the prior art. German Patent 22 41 535, for example, describes a coating material for flat textile articles based on epoxidation products of esters of unsaturated fatty acids and polyvalent aliphatic alcohols.

However, the epoxidized oils and fatty acids used in such a method

are liquid in the unprocessed state, with the result that flat articles cannot be molded from said substances in the raw state. Thus, in the production of flat articles from such a material it is common to carry out pre-crosslinking of the oils and/or fatty acids to give a highly viscous, moldable intermediate product (prepolymer). After molding into flat articles, a second crosslinking step is then carried out to give a usable material (final crosslinking). Termination of the first crosslinking step is problematic. In principle, a two-step reaction can be carried out in the following manner:

- (I) Pre-crosslinking in which one of the crosslinking components is present in deficit (epoxidation product or crosslinking agent). Full crosslinking is carried out with addition of the component present in deficit.
- (II) Different temperatures in the individual process steps.
- (III) Use of separate crosslinking agents having different reactivities.
- (IV) Different mechanisms in both process steps.

International Patent WO 90/107607 describes a method in "two reaction phases," whereby in the first reaction phase a mixture of a stand oil with fillers is homogenized, then partially polymerized and partially crosslinked at elevated temperatures, using a peroxide, to give an intermediate product. The powdered intermediate product is then homogenized with an elastomeric natural or synthetic material, fillers, and a peroxide, and is again crosslinked and polymerized at elevated temperature.

Coating materials that are based on renewable raw materials and used for coating flat textile articles or release paper are known from German Patent Application 41 35 664. The coating materials are composed of a combination of epoxidation products of esters of unsaturated fatty acids and partial esters of polycarboxylic acids with polyether polyols in addition to a hydrophobing agent. These coating materials are used for the production of floor coverings. It is disadvantageous, however, that the top layer of coverings produced in this way is very rough and non-transparent. Furthermore, the surface of these coverings is not sufficiently soil-repellent and exhibits poor through-hardening.

Spreadable coating materials for the production of flat articles based on renewable raw materials are known from International Patent WO 96/15203. However, due to the use of so-called "coating pastes" contained in the coating materials, the production of said flat articles is limited to coating methods.

International Patent WO 98/28356 describes a method for producing flat articles based on renewable raw materials, in which flat articles with satisfactory material properties can be obtained by pressing, calendering, or extruding. An intermediate product that can be stored (prepolymer) is obtained, however, only if either the crosslinking agent or the epoxidation product is present in deficit. The prepolymer is converted to the fully crosslinked material in the second crosslinking step by addition of the component that is present in deficit. This method has the disadvantage that a considerable portion of the component first added in deficit must be compounded into the already viscous, pre-crosslinked material.

Since the reactions underlying pre-crosslinking and final crosslinking in the prior art are always based on the same reaction mechanism, it is difficult to obtain a further processable, storable intermediate product by timely termination of pre-crosslinking or by use of a component in deficit.

The object of the present invention, therefore, is to provide a novel method for producing a flat article from renewable raw materials in which essentially no ripening time is necessary and in which the rate of pre-crosslinking can be better regulated. A further object is that the pre-crosslinked intermediate product has a practically unlimited storage life.

This object is achieved by the embodiments characterized in the claims.

In particular, a method for producing a flat article comprising a

material that contains polyreaction products is provided which comprises the following steps:

- (1) Compounding of an epoxidation product of at least one carboxylic acid ester using at least one crosslinking agent,
- (2) Pre-crosslinking or partial crosslinking of the mixture obtained in step (1) to form a moldable material,
- (3) Molding of the moldable material obtained in step (2) in the shape of a flat article, and
- (4) Curing, further crosslinking, or final crosslinking of the molded material to produce the flat article,

wherein the pre-crosslinking reaction in step (2) is separate from the curing reaction in step (4).

The present invention is based on the knowledge that the disadvantages of known methods of the prior art can be avoided by having separate chemical reactions or chemical reaction mechanisms for pre-crosslinking and for curing. To this end, at least two different reactions I and II occur in the mixture obtained by compounding (1), for example by the presence of at least two crosslinkable groups A and B. For pre-crosslinking in step (2), essentially only one reaction I proceeds, for example by reaction of only one crosslinkable group A, that is, a class of similar crosslinkable groups. Reaction II, which is different from reaction I, does not proceed significantly under the reaction conditions for pre-crosslinking. For example, group B, which is different from A, is essentially stable or inert under the reaction conditions for pre-crosslinking, and in this step is practically unreacted. Reaction I, for example, halts after the consumption—that is, the essentially complete reaction—of group A to produce the moldable material. Furthermore, a suitable agent can be used to terminate reaction I after a desired reaction rate is achieved to produce the moldable material.

According to the invention, the second crosslinking step, that is, reaction II—the

reaction of group B, for example—is initiated or started only by modification of the reaction conditions. In the context of the present invention, “modification of the reaction conditions” means an elevation in temperature or an increase or decrease in pressure, addition of reaction-initiating agents such as radical-forming initiators, and/or exposure of the mixture obtained in step (1) or the partially crosslinked material obtained by pre-crosslinking (2) to radiation, such as UV, electron beam, or IR radiation.

For example, pre-crosslinking (2) can be carried out at a relatively low temperature T_1 , optionally with radiation, at which reaction I proceeds, and group A, for example, is at least partially reacted, for example by esterification or etherification or a condensation, substitution, or addition reaction, optionally associated with a ring opening. At this temperature T_1 , reaction II does not proceed to a significant extent, and there is practically no conversion of group B, for example. For final crosslinking, at a specified time the moldable material can be heated to a higher temperature T_2 at which reaction II, for example a radical crosslinking of group B, is initiated, such as by decomposition of a heat-sensitive group B itself or by a radical initiator that decomposes only at a temperature T_2 . In addition, the mixture obtained in step (1) during pre-crosslinking (2) can be exposed to radiation, for example UV radiation, which has brought about reaction I, for example crosslinking of group A. In contrast, crosslinking of group B is initiated only by an increase in temperature or another type of radiation such as IR or electron beam radiation or UV radiation at another wavelength, during final crosslinking (4). Also, the addition of, for example, radical- or ion-forming initiators or exposure to an atmosphere containing a reactive gas such as oxygen can be understood as modification of the reaction conditions according to the invention.

A major advantage of the present invention, therefore, is that in

a preferred embodiment the pre-crosslinking automatically terminates after reaction of the first crosslinkable groups is complete, and as a rule, appreciable crosslinking by the second crosslinkable groups beyond a moldable product does not occur in this step.

The epoxidation product of at least one carboxylic acid ester is preferably the epoxidation product of one or several esters of unsaturated fatty acids, preferably an epoxidized natural triglyceride or a derivative thereof. Epoxidized linseed oil, epoxidized soybean oil, epoxidized castor oil, epoxidized rapeseed oil, or vernonia oil or a mixture containing at least two of these epoxidation products can be used, for example. In one embodiment these epoxidation products are only partially epoxidized; that is, in addition to epoxidized double bonds there remain unreacted double bonds in the carboxylic acid ester. The alcohol component of these carboxylic acid esters is not subject to any particular limitation. Dipropylene glycol, propanediols, butanediols, hexanediols, hexanetriols, glycerin, or pentaerythritol are examples of alcohol components that can be used. The carboxylic acid component is not subject to any particular limitation.

According to the present invention, the mixture obtained in step (1) is crosslinked in two crosslinking steps (2) and (4). In the first crosslinking step (2) a moldable intermediate product that can be stored is produced from liquid raw materials, for example. This crosslinking step (2) can be carried out after the compounding step (1) as well as simultaneously with the compounding step (1). After molding (3) in the shape of a flat article, the intermediate product acquires its final functional properties through curing and the second crosslinking step (4).

Furthermore, according to the invention the pre-crosslinking reaction is separate from the curing reaction. For example, when partially epoxidized carboxylic acid esters of unsaturated fatty acids are used in a first crosslinking step, the epoxy groups are preferably completely reacted, and in a second crosslinking step the remaining unsaturated double bonds

are crosslinked by radical polymerization, for example. In particular, the second crosslinking step can be carried out using essentially completely epoxidized carboxylic acid esters via radical hydrogen abstraction of the pre-crosslinked material, and recombination.

Reaction of the epoxy groups preferably is carried out with at least bifunctional compounds, so-called "crosslinking agents," for example by nucleophilic attack and addition to the epoxy group.

According to the present invention, the term "crosslinking" encompasses an increase in molar mass or molecular size. For example, the term "crosslinking" is associated with an increase in viscosity of the moldable material in comparison to the mixture obtained in step (1).

According to one embodiment of the present invention, so-called "acid crosslinking agents," that is, di- or polycarboxylic acids or derivatives thereof, are used as reactants in such a reaction. In one embodiment, such di- or polycarboxylic acids or derivatives thereof contain at least one double bond per molecule. Maleic acid, itaconic acid, fumaric acid, succinic acid, methylsuccinic acid, malic acid, phthalic acid, tartaric acid, citraconic acid, furandicarboxylic acid, or a mixture of at least two of said acids are preferably used as dicarboxylic acids. Acids containing three or more carboxylic acid groups, such as citric acid, aconitic acid, and trimellitic acid, are preferably used as polycarboxylic acids.

Anhydrides or partial esters or derivatives having at least one free carboxylic acid group can be used as derivatives of di- or polycarboxylic acids. The alcohol component of the partial esters is not subject to any particular limitation; however, polyols such as dipropylene glycol, propanediols, butanediols, hexanediols, hexanetriols, glycerin, or pentaerythritol are preferably used as the alcohol component.

In one embodiment, a mixture of a partial ester of maleic acid anhydride and dipropylene glycol together with citric acid as crosslinking agent is used, where the amount of citric acid is less than or equal to 50 wt%, preferably less than or equal to 25 wt%, relative to the total quantity of crosslinking agent.

Moreover, the crosslinkable groups required for curing (4) may be introduced via the crosslinking agent.

The reaction of the epoxidation product with the crosslinking agent is preferably induced thermally and/or by radiation. In the case of thermal induction, the reaction is carried out, for example, at a temperature ranging from room temperature to 280°C, preferably from room temperature to 200°C, in particular to a temperature of 150°C. UV radiation, electron beam radiation, and/or IR radiation may be used as the reaction-inducing radiation.

A reaction induced by UV radiation should be carried out in the presence of at least one UV initiator, and with electron beam radiation the addition of at least one UV initiator may be omitted. The UV initiators that may be used according to the invention can be radical or cationic UV initiators or a mixture of these types of UV initiators. Preferred examples of radical UV initiators include benzophenone, benzophenone derivatives, phosphine oxides, α -morpholinoketones, quinone, quinone derivatives, α -hydroxyketones, or mixtures thereof. Preferred examples of cationic UV initiators include triarylsulfonium salts, which can be present as one type or as a mixture of different triarylsulfonium salts, or diaryliodonium salts or mixtures thereof. The UV initiators are present, for example, in quantities of less than or equal to 15 wt%, preferably 0.05 to 8 wt%, relative to the quantity of the material containing polyreaction products.

In one embodiment according to the invention, in addition to the UV initiator at least one photosensitizer, such as a compound based on anthracene, perylene, or thioxanthene-9-one, is present which

activates the UV initiator and which can intensify the effect thereof. The concentration of the UV initiator can thus be reduced. UV radiation used according to the invention lies in a generally common range, that is, between 200 nm and 380 nm. IR radiation used according to the invention lies in a generally common range, for example between 760 nm and 0.5 mm.

The material containing polyreaction products preferably comprises 10 to 99 wt% binders relative to the total quantity of the material containing polyreaction products. The term "binder" encompasses the crosslinking monomer and prepolymer components as well as crosslinking agents. In the mixture obtained in step (1), the respective weight quantities of the crosslinking agent and the epoxidation product are preferably 5 to 80 wt%, relative to the total quantity of the material containing polyreaction products.

Furthermore, in compounding step (1) additional additives or components, such as fillers, titanium dioxide, pigments for embossing, hydrophobing agents, auxiliary agents, and possibly co-crosslinking agents such as triallylisocyanurate, triallylcyanurate, ethylene glycol dimethacrylate, trimethylolpropane-trimethacrylate, and *m*-phenylene-bis-maleinimide may be admixed. The fillers are preferably wood dust, chalk, cork powder, barium sulfate, silicic acid, kaolin, quartz-kaolinite mixture, talc, glass, textile fibers, glass fibers, plant fibers, cellulose fibers, or polyester fibers, and nanoscale "intelligent" fillers such as organically modified bentonites. Examples of auxiliary agents that may be used include tall oils, synthetic or natural resins such as balsamic resins, copal resins, or hydrocarbon resins, and/or desiccants such as compounds of the metals Al, Li, Ca, Ba, Fe, Mg, Mn, Pb, Zn, Zr, Ce, Sn, or Co, or a combination containing at least two of these compounds.

As a result of pre-crosslinking (2) of the partially liquid components, the intermediate product formed has a specific pre-crosslinking rate and quasi-thermoplastic properties and is therefore moldable. Since reaction I,

for example the reaction of the first crosslinkable groups A, proceeds essentially to completion and curing according to the invention can be performed only by modifying the reaction conditions by initiating reaction II, for example by crosslinking of second crosslinkable groups B, the moldable intermediate product surprisingly has a practically unlimited storage life. The partially cured material can be comminuted (granulated or powdered) after the pre-crosslinking step (2), and can be stored in powdered form, for example.

The term "moldable material" applied to an intermediate product in this context means an essentially liquid reaction product as well as a highly viscous reaction product as binder. According to the present invention, the crosslinking rate of the pre-crosslinked moldable material obtained in step (2) is less than the crosslinking rate of the material containing polyreaction products in the form of a flat article obtained after curing (4).

The crosslinking rate of the moldable material can be controlled by the ratio of the number of first crosslinkable groups to the number of second crosslinkable groups, without significantly influencing the overall number of crosslinking groups and thus the crosslinking rate of the end product. If the relative number of first crosslinkable groups is relatively small, a rather low-viscosity moldable material is obtained as the intermediate product. If the relative number of first crosslinkable groups is larger, an intermediate product with a more solid consistency is obtained which can be processed as a granulate or powder, for example. In the case of epoxidation products of carboxylic acid esters of unsaturated fatty acids, the ratio of epoxy groups to unsaturated double bonds can be controlled, for example, by the epoxidation rate or via hydrogen abstraction by the peroxide dosage during crosslinking.

In addition, the consistency of the moldable material obtained in step (2) is influenced by whether a bifunctional or trifunctional crosslinking agent, for example, is used. Of course, the consistency also depends on the type and quantity

of additional components compounded, such as fillers, for example.

An advantage of the method according to the invention, therefore, is that the moldable pre-crosslinked material obtained in step (2) can be processed into a flat article using common methods such as pressing, calendering, or extruding.

Molding (3) of the compounded material can be carried out before curing (4) or simultaneously with curing (4). The pre-crosslinked material can be shaped in customary processing machines such as presses, double band presses, calenders, adaptive universal multiple access (AUMA) facilities, or thermoset machines, or by extruders with slot dies. for example. In addition, for embossing, differently colored chips or granules of an otherwise practically identical material can be interspersed in the material web obtained, whereupon the web can be given its final shape in a calender, AUMA facility, or thermoset machine, etc., for example.

Furthermore, an embossing method can be used in which, before curing (4), a patterned or printed absorbent material is applied to the material molded as a flat article. To avoid stresses in the flat article, material of the same type, which optionally is printed, may optionally be applied to the reverse side as a countermeasure. The absorbent material is preferably a cellulose non-woven fabric made of reclaimed cellulose fibers having a high specific surface, for example, which is characterized by high absorptivity, high dry and wet strengths, and low shrinkage. The weight per unit area of such cellulose non-woven fabrics ranges from 25 to 50 g/m², for example. During subsequent pressing, a portion of the not yet fully crosslinked binder according to the invention penetrates the absorbent material and forms a thin top layer or wear layer after curing, which optionally can be lacquered by customary methods on the top side of the flat article embossed in such a manner. The top layer or wear layer of the patterned or printed material is thereby protected from abrasion.

One advantage of such a one-step embossing method is that a flat article constructed from the material defined above may be imprinted as desired, which for flat articles made of linoleum, for example, is not applicable.

According to the present invention, the intermediate product can be further crosslinked and cured in a second crosslinking step, either after or simultaneously with molding. Curing (4) may be performed by common methods such as pressing, for example by using a jaw press, AUMA facility, double band press, or calendering method, by simple passage through a heated channel, or by a combination of these methods, optionally at elevated temperature.

According to one embodiment, curing (4) can be performed by peroxidic crosslinking via radical hydrogen abstraction. In this reaction, a radical initiator is added that decomposes to form radicals. Each radical created directly or in a consecutive reaction can remove one hydrogen from the pre-crosslinked material, thereby becoming saturated. A radical site is simultaneously formed on a macromolecule of the pre-crosslinked material. Two macromolecular radicals formed in this manner can join to form a new C-C bond. Multiple repetitions of this process on the pre-crosslinked material results in the final crosslinked material containing polyreaction products. The speed of this reaction is determined by the peroxide decomposition rate. Because such peroxidic crosslinking proceeds stoichiometrically and not as a chain reaction, the rate of final crosslinking can be controlled by the peroxide dosage. The amount of peroxide required depends on the desired end properties of the material containing polyreaction products, the type of peroxide, the form of delivery, and the type and quantity of the additional additives. Preferably, 0.05 to 10 wt% peroxide, in particular 0.5 to 10 wt%, relative to the weight of the binder, is used. Preferred peroxides include acyl peroxide, perketals, and aryl, alkyl, and aralkyl peroxides, or peroxides that release aroyl, phenyl, alkoxy, aralkoxy, or primary alkyl radicals.

Dicumyl peroxide, tert-butylcumyl peroxide, di(2-tert-butylperoxyisopropyl)benzene, di(tert-butyl)peroxide, 1,1-di(tert-butylperoxy)-3,3,5-trimethylcyclohexane, 2,5-bis(tert-butylperoxy)-2,5-dimethylhexane, and 2,5-bis(tert-butylperoxy)-2,5-dimethylhexyne(3), for example, are particularly preferred. In addition, crosslinking can be carried out with the addition of sulfur or silicon compounds singly or in combination with the peroxides listed above. The peroxide decomposition reaction can be induced thermally as well as by radiation, for example by UV radiation. This reaction is preferably thermally initiated. If the peroxides are already contained in the mixture, prior to the actual crosslinking the pre-crosslinked material should not be heated above a temperature at which little or no crosslinking is observed within the typical reaction time (so-called "scorch temperature").

According to a further embodiment, the curing reaction comprises a radical crosslinking of the free double bonds of the partially epoxidized carboxylic acid ester or of the double bonds of the crosslinking agent. In particular, organic peroxides commonly used as radical initiators or azobis compounds in customary forms of use can be used as radical-forming initiators or starters for curing (4). Examples of such include hydroperoxides such as cumene hydroperoxide and t-butylhydroperoxide, peroxyesters such as t-butylperoxybenzoate, t-butylperoxy-3,5,5-trimethylhexanoate, t-butylperoctoate, and dimyristylperoxydicarbonate, peroxyketals such as 1,1-bis(t-butylperoxy)-3,3,5-trimethylcyclohexane and 1,1-bis(t-butylperoxy)cyclohexane, dialkylperazides and diaralkylperoxides such as di-t-amyl peroxide, dicumyl peroxide, and 2,5-bis(t-butylperoxy)-2,5-dimethylhexane and -hexyne(3), and azobis compounds such as 2,2'-azobis(2-acetoxyp propane) and 2,2'-azo-bis(2-methylpropionitrile). The radical chain reaction can be initiated thermally as well as by radiation, by UV radiation, for example.

The radical-forming initiator is preferably admixed with the other components in the form of a mixture with a mineral oil. Such a mineral oil acts as a wetting agent for the

granulate and can simultaneously have a desensitizing effect.

The radical-forming initiator can optionally be compounded with the other components of the material in the compounding step (1) and/or before pre-crosslinking (2) and/or before molding of the flat article (3) in a second optional compounding step, or the radical-forming initiator can be incorporated by compounding before both crosslinking steps. Before shaping onto the surface of the appropriate material is performed, the radical-forming initiator, for example one of the aforementioned peroxides, can also be applied substantially to the surface by spraying, for example. Peroxides with different half lives and/or decomposition temperatures may optionally be added, so that, for example, decomposition of the peroxide required in the second crosslinking step (4) for curing does not occur during the first crosslinking step (2) of the method according to the invention.

Compounding (1) of the components is preferably carried out in an extruder or mixer. Furthermore, the method according to the invention may optionally include a second compounding step, such as the addition of peroxide, before molding of the flat article.

Surprisingly, the flat articles obtained by the method according to the invention are crosslinked throughout their entire cross section without further ripening, are non-tacky and flexible, and have a high bend restoring force; that is, they can be used directly after production. Hence, omission of the ripening process enables the method according to the invention to be carried out continuously.

The method according to the invention may optionally include an embossing step for the cured flat article, using the thermal transfer printing method, for example, known in the art.

The present invention further relates to a moldable, storable material that can be obtained through steps (1) and (2) of the method according to the invention.

This intermediate product has the composition described above.

The invention further relates to a flat article that can be obtained from the moldable, storable material according to the invention by molding and curing.

The flat articles produced by the method according to the invention are preferably used as floor or wall coverings. The flat articles can be present in a homogeneous form, or the pre-crosslinked material can be applied onto a substrate such as glass fiber mat, cardboard, jute fabric, or a substrate based on jute, such as mixtures of jute mat and polypropylene/polyester non-woven fabric.

The following example explains the present invention in more detail.

Example

Formulation: 41.0 wt% epoxidized natural triglyceride
 8.2 wt% acid crosslinking agent
 41.0 wt% filler
 8.2 wt% white pigment
 1.6 wt% peroxide/mineral oil mixture (1 : 2)

Procedure:

The solid materials were weighed together and mixed. In a parallel procedure the peroxide/mineral oil mixture was added to the epoxidized natural triglyceride and admixed. Both mixtures were then purified and homogenized over a period of 5 minutes in a laboratory dissolver. Curing was then carried out in a first stage in a metering mixer over a period of 25 minutes at 160°C. The still moldable material thus obtained was formed into pressed plates in a hydraulic two-jaw press, using a metal frame 1.5 mm thick having a surface area of 169 cm², and silicone separating tissue. The stamping pressure of the press was approximately 30 bar, the jaw temperature was 200°C, and the crosslinking time was 15 minutes.

The plates thus obtained were crosslinked throughout their entire cross section, were non-tacky and flexible, and had a high bend restoring force.

Claims

1. Method for producing a flat article comprising a material that contains polyreaction products, comprising the following steps:
 - (1) Compounding of an epoxidation product of at least one carboxylic acid ester using at least one crosslinking agent,
 - (2) Pre-crosslinking of the mixture obtained in step (1) to form a moldable material,
 - (3) Molding of the moldable material obtained in step (2) in the shape of a flat article, and
 - (4) Curing of the molded material to produce the flat article,wherein the pre-crosslinking reaction in step (2) is separate from the curing reaction in step (4).
2. Method according to Claim 1, characterized in that an epoxidized carboxylic acid ester of unsaturated fatty acids is used as the epoxidation product.
3. Method according to Claim 1 or 2, characterized in that epoxidized linseed oil, epoxidized soybean oil, epoxidized castor oil, epoxidized rapeseed oil, or vernonia oil or a mixture thereof containing at least two different epoxidation products is used as the epoxidation product.
4. Method according to one Claims 1 through 3, characterized in that pre-crosslinking is carried out essentially by reacting the epoxy groups of the epoxidation product.
5. Method according to one Claims 1 through 4, characterized in that a di- or polycarboxylic acid, or a derivative thereof, or a mixture containing

at least two different crosslinking agents is used as the crosslinking agent.

6. Method according to Claim 5, characterized in that maleic acid, itaconic acid, fumaric acid, succinic acid, methylsuccinic acid, malic acid, phthalic acid, tartaric acid, citraconic acid, furandicarboxylic acid, or a mixture of at least two of said acids is used as the dicarboxylic acid.
7. Method according to Claim 6, characterized in that citric acid, trimellitic acid, or aconitic acid is used as the polycarboxylic acid.
8. Method according to one of Claims 5 through 7, characterized in that an anhydride or partial ester is used as the derivative of a di- or polycarboxylic acid.
9. Method according to one of the preceding claims, characterized in that the reaction of the epoxidation product with the crosslinking agent is induced thermally and/or by radiation.
10. Method according to Claim 9, characterized in that the reaction induced by radiation is carried out by using UV radiation in the presence of at least one UV initiator and/or by using electron beam radiation optionally in the presence of at least one UV initiator, and/or by using IR radiation.
11. Method according to one of the preceding claims, characterized in that an additional compounding step is included before step (3).
12. Method according to one of the preceding claims, characterized in that in step (1) or before step (3) at least one additional additive from the group comprising fillers, pigments, hydrophobing agents, and auxiliary agents is incorporated by compounding.
13. Method according to one of the preceding claims, characterized in that the curing of the moldable material is performed by peroxidic crosslinking via radical hydrogen abstraction and/or by radical polymerization

of unsaturated double bonds.

14. Method according to Claim 13, characterized in that the hydrogen abstraction and/or radical polymerization of unsaturated double bonds is initiated by radical-forming initiators selected from organic peroxides or azobis compounds or a mixture thereof.
15. Method according to Claim 14, characterized in that the radical-forming initiators are incorporated by compounding in step (1) and/or before step (2) and/or before step (3).
16. Method according to one of the preceding claims, characterized in that pre-crosslinking and curing are carried out at different temperatures.
17. Moldable material that can be stored, which can be obtained by steps (1) and (2) of the method as defined in Claims 1 through 16.
18. Flat article which can be obtained by the method as defined in Claims 1 through 16.

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum
Internationales Büro



(43) Internationales Veröffentlichungsdatum
1. Februar 2001 (01.02.2001)

PCT

(10) Internationale Veröffentlichungsnummer
WO 01/07519 A1

(51) Internationale Patentklassifikation⁷: C08L 67/08,
C08J 3/24, D06N 3/16

(74) Anwalt: PERREY, Ralf; Müller-Boré & Partner, Grafing-
er Strasse 2, D-81671 München (DE).

(21) Internationales Aktenzeichen: PCT/EP00/06573

(81) Bestimmungsstaaten (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(22) Internationales Anmeldedatum:
11. Juli 2000 (11.07.2000)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
199 34 036.6 21. Juli 1999 (21.07.1999) DE

(84) Bestimmungsstaaten (*regional*): ARIPO-Patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI-Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Anmelder (*für alle Bestimmungsstaaten mit Ausnahme von US*): DLW AKTIENGESSELLSCHAFT [DE/DE]; Stuttgarter Strasse 75, D-74321 Bietigheim-Bissingen (DE).

Veröffentlicht:

- Mit internationalem Recherchenbericht.
- Vor Ablauf der für Änderungen der Ansprüche geltenden Frist; Veröffentlichung wird wiederholt, falls Änderungen eintreffen.

(72) Erfinder; und

(75) Erfinder/Anmelder (*nur für US*): FISCHER, Bernd [DE/DE]; Marichweg 8, D-71546 Aspach (DE). HAMANN, Heiko [DE/DE]; Taubenstrasse 6, D-74392 Freudental (DE). MAUK, Hans-Jörg [DE/DE]; Dammweg 2, D-74395 Mundelsheim (DE). ESS, Miko [DE/DE]; Kniestedtstr. 22, D-71691 Freiburg (DE). KASTL, Bernd [DE/DE]; Nelkenweg 18, D-74321 Bietigheim-Bissingen (DE).

Zur Erklärung der Zweibuchstaben-Codes, und der anderen Abkürzungen wird auf die Erklärungen ("Guidance Notes on Codes and Abbreviations") am Anfang jeder regulären Ausgabe der PCT-Gazette verwiesen.

(54) Title: METHOD FOR PRODUCING FLAT ARTICLES FROM RENEWABLE RAW MATERIALS

(54) Bezeichnung: VERFAHREN ZUR HERSTELLUNG VON FLÄCHENGEBILDEN AUS NACHWACHSENDEN ROHSTOFFEN

(57) Abstract: The present invention relates to a method for producing a flat article comprising a material that contains the products of several reactions. The method comprises the following steps: carrying out a pre-cross-linking of a mixture comprising an epoxydation product of a carboxylic acid ester using at least one cross-linking agent in order to form a mouldable material; moulding the mouldable material in the shape of a flat article; and curing the moulded material in order to produce a flat article, wherein the pre-cross-linking reaction is separate from the curing reaction. This invention also relates to a mouldable material that can be stored and to a flat article that can be obtained from the same.

(57) Zusammenfassung: Die vorliegende Erfindung betrifft ein Verfahren zur Herstellung eines Flächengebildes mit einem Polyreaktionsprodukte-enthaltenden Material, umfassend das Vorvernetzen einer Mischung eines Epoxidierungsprodukts von mindestens einem Carbonsäureester mit mindestens einem Vernetzer zu einer formbaren Masse, Formen der formbaren Masse in ein Flächengebilde und Aushärten der formbaren Masse unter Erhalt des Flächengebildes, worin die Vorvernetzungsreaktion unterschiedlich zur Aushärtungsreaktion ist. Die Erfindung betrifft ferner eine formbare, lagerfähige Masse und ein aus dieser formbaren, lagerfähigen Masse erhältliches Flächengebilde.

WO 01/07519 A1

D 2874-py

DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

As the below named inventors, we hereby declare that:

Our residence, post office address and citizenship are as stated below next to our names;

We believe we are the original, first and joint inventors of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**METHOD FOR PRODUCING FLAT ARTICLES FROM RENEWABLE RAW
MATERIALS** ✓

the specification of which was filed on 11 July 2000 ✓ as Application Serial No. PCT/EP00/06573. ✓

We hereby state that we have reviewed and understand the contents of the above identified specification, including the claims.

We acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

We hereby claim any foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) and/or any international priority benefits under Title 35, United States Code, §365 based on the following foreign and/or international application(s) listed below, and also identify below any foreign and/or international application(s) for patent or inventor's certificate having a filing date before that of the application(s) on which priority is claimed:

Prior Foreign Application(s): German Application 19934036.6, Filed: 21 July 1999. ✓

We hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, we acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing of the prior application and the national or PCT international filing date of this application:

Prior Application(s): None.

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States

Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

14- We hereby appoint: Louis T. Isaf, Registration No. 29,078; James F. Vaughan, Registration No. 31,889; Steven D. Kerr, Registration No. 32,472; David Scott Sudderth, Registration No. 34,026; John J. Timar, Registration No. 32,497; Michael A. Cicero, Registration No. 34,562; Steven L. Schmid, Registration No. 39,358; David Hayzer, Registration No. 43,329; David S. Bradin, Registration No. 37,783; Jacquelyn D. Austin, Registration No. 43,478; Carl B. Massey, Jr., Registration No. 44,224; Brian J. Hairston, Registration No. 46,750; Thomas B. McGurk, Registration No. 44,920; and Kathleen Neuner Manne, Registration No. 40,101 having as their mailing address Womble Carlyle Sandridge & Rice, PLLC, P.O. Box 7037, Atlanta, Georgia 30357-0037, our attorneys jointly and severally, with full power of substitution and revocation, to prosecute this application, to make alterations and amendments therein, to receive the patent, and to transact all business in the Patent Office connected therewith, all correspondence to be directed to the said Steven L. Schmid, Womble, Carlyle Sandridge & Rice, PLLC, P.O. Box 7037, Atlanta, Georgia 30357-0037.

1-00 Inventor's Signature: Bernd Fischer

Full Name of Inventor: Bernd Fischer

Date: 24.01.02

Citizenship: Germany ✓

Residence Address: Marichweg 8, D-71546 Aspach, Germany DEX

Post Office Address: Marichweg 8, D-71546 Aspach, Germany

Inventor's Signature: Heiko Hamann

2-00 Full Name of Inventor: Heiko Hamann

Date: 25.1.02

Citizenship: Germany ✓

Residence Address: Taubenstrasse 6, D-74392 Freudental, Germany DEX

Post Office Address: Taubenstrasse 6, D-74392 Freudental, Germany

Inventor's Signature: [Signature]

3-00 Full Name of Inventor: Hans-Jörg Mauk

x Date: 25.01.02

Citizenship: Germany ✓

Residence Address: Dammweg 2, D-74395 Mundelsheim, Germany **DEX**

Post Office Address: Dammweg 2, D-74395 Mundelsheim, Germany

Inventor's Signature: [Signature]

4-00 Full Name of Inventor: Miko Ess

Date: 24/1/02

Citizenship: Germany ✓

Residence Address: Kniestedtstr. 22, D-71691 Freiburg, Germany **DEX**

Post Office Address: Kniestedtstr. 22, D-71691 Freiburg, Germany

Inventor's Signature: [Signature]

5-00 Full Name of Inventor: Bernd Kastl

Date: 24.1.2002

Citizenship: Germany ✓

Residence Address: Nelkenweg 19, D-74321 Bietigheim-Bissingen, Germany **DEX**

Post Office Address: Nelkenweg 19, D-74321 Bietigheim-Bissingen, Germany

Docket No: D078 1160.1